



Sample Result Name	Type	Measure Date Time	Recalculation Date Time	Origin	Method Name
Galeno_RML/148/1	Unknown	22-06-2025 20:33:42	22-06-2025 20:33:42	Measured	Pb-Remelted Lead (Galeno Metallics)

Method Version	Operator Name	Correction Type	Type Corr Sample Name	Check Type	Check Status
		None		None	NotUsed

Grade Verification Name	Grade Verification Similarity	Grade Search Name	Grade Search Similarity
	0.00000 %		0.00000 %

Sample Name	Batch No	Heat Number		
INITIAL	148	1		

Elements Conc.

Meas.	Sn	Ag	Sb	Bi	Cd	Al	As
	%	%	%	%	%	%	%
	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.
1	0.14149	0.00213	0.82523	0.01076	0.00168	0.00013	0.05538
<>	0.14149	0.00213	0.82523	0.01076	0.00168	0.00013	0.05538

Meas.	Ca	Cu	Fe	Ni	P	S	Te
	%	%	%	%	%	%	%
	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.
1	0.00010	0.00758	0.00038	0.00064	0.00650	0.00973	0.00094
<>	0.00010	0.00758	0.00038	0.00064	0.00650	0.00973	0.00094

Meas.	Zn	Na	Mg	Pd	Pb	Se	
	%	%	%	%	%	%	
	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	
1	0.00036	0.00019	0.00009	<0.00005	98.9359	0.00075	
<>	0.00036	0.00019	0.00009	<0.00005	98.9359	0.00075	